

### Magnetic Properties of SmCo Magnets (Samarium Cobalt)

Material	Grade	Remanence		Coercivity		Intrinsic Coercivity		Max. Energy Product	
		Br(mT)	Br(kGs)	bHc(kA/m)	bHc(kOe)	iHc (kA/m)	iHc (kOe)	(BH) <sub>max</sub> (KJ/m <sup>3</sup> )	(BH) <sub>max</sub> (MGOe)
SmCo <sub>5</sub>	S16	750-800	7.5-8.0	557-637	7.0-8.0	1989	25	111-143	14-18
	S18	800-930	8.0-9.3	597-677	7.5-8.5	1432	18	127-159	16-20
	S20	850-980	8.5-9.8	597-677	7.5-8.5	1273	16	143-175	18-22
	S24	1000	10.0	680	8.5	1195	15	175-190	22-24
Sm <sub>2</sub> Co <sub>17</sub>	S180	900-1030	9.0-10.3	597-677	7.5-8.5	1194	15	127-159	16-20
	S22A	900-1030	9.0-10.3	613-693	7.7-8.7	1989	25	159-191	20-24
	S22B	900-1030	9.0-10.3	613-693	7.7-8.7	1432	18	159-191	20-24
	S240	980-1080	9.8-10.8	636-716	8.0-9.0	1432	18	175-207	22-26
	S26A	1000-1130	10.0-11.3	676-756	8.5-9.5	1194	15	191-223	24-28
	S26B	1000-1130	10.0-11.3	676-756	8.5-9.5	796	10	191-223	24-28
	S280	1030-1130	10.3-11.3	716-796	9.0-10.0	1432	18	207-239	26-30
	S270	1000-1100	10.0-11.0	357-516	4.5-6.5	413	5.2	183-223	24-28
S300	1100-1200	11.0-12.0	438-517	5.5-6.5	454	5.7	223-255	28-32	

### HARD FERRITE (CERAMIC MAGNETS)

As important parts of magnetic materials, hard ferrite (ceramic) magnets play an important role in electrical, electronic information, car, motorcycle industries etc. They are also widely used in medical treatment, mining and metallurgy, industrial automation, oil energy and civil industries.

Ceramic magnets are composed of iron oxide, barium and strontium elements. This class of magnets has a higher magnetic flux density, higher coercive force, and higher resistance to demagnetization and oxidation compared to other non-rare earth permanent magnets. The biggest advantage of such magnets is the low cost, which makes the hard ferrite magnets very popular in many permanent magnet applications. Due to their ceramic nature, ferrite magnets are very hard and brittle. Special machining techniques must to be utilized for these magnets. Ceramic or hard ferrite magnets come in discs, cylinders, rings, blocks and arcs and are charcoal grey.

Widely used in electrical appliances, educational instruments, magnetic assemblies, toys etc.



#### Material Information

- Produced by powder metallurgical method with chemical composition of Ba/SrO.6 Fe<sub>2</sub> O<sub>3</sub>.
- Relatively brittle & hard.
- Good resistance to demagnetization.
- Excellent corrosion resistance.
- Raw material is readily available and low in cost.
- Good temperature stability.
- high coercive force and high electric resistance.
- Most widely used permanent magnets.

#### Typical Physical Properties

Curie Temperature (°C)	450
Maximum Operating Temperature (°C)	250
Hardness (Hv)	480-580
Density (g/cm <sup>3</sup> )	4.8 - 4.9
Relative Recoil Permeability (μ <sub>rec</sub> )	1.05 - 1.20
Saturation Field Strength, kOe (kA/m)	10 (800)
Temperature Coefficient of Br (%/°C)	-0.2
Temperature Coefficient of iHc (%/°C)	0.3
Tensile Strength (N/mm)	<100
Transverse Rupture Strength (N/mm)	300



## Dimension Range / Nominal Tolerance of Ceramic / Hard Ferrite Magnets

Ring Magnet	Outer Diameter (mm)	Inner Diameter (mm)	Thickness (mm)
Maximum	220	110	40
Minimum	2.6	1.8	0.5
Tolerance	±0.2	±0.15	±0.1
Block Magnet	Length (mm)	Width (mm)	Thickness (mm)
Maximum	220	200	40
Minimum	2.0	1.5	0.5
Tolerance	±0.2	±0.15	±0.1
Disc/Cylinder Magnet	Diameter (mm)	Thickness (mm)	±0.1
Maximum	220	40	
Minimum	1.2	0.5	
Tolerance	±0.2	±0.1	

## Magnetic Properties of Hard Ferrite (Ceramic) Magnets

Material	Remanence		Coercivity		Intrinsic Coercivity		Max. Energy Product	
	Br (mT)	Br (kGs)	bHc (kA/m)	bHc (kOe)	iHc (kA/m)	iHc (kOe)	(BH) <sub>max</sub> (KJ/m <sup>3</sup> )	(BH) <sub>max</sub> (MGOe)
Y10	200-235	2.00-2.35	125-160	1.57-2.01	210-280	2.64-3.52	6.5-9.5	0.8-1.2
Y10T	>200	>2.00	128-160	1.60-2.00	128-160	1.60-2.00	6.4-9.6	0.8-1.2
Y20	320-380	3.20-3.80	135-190	1.70-2.38	140-195	1.76-2.45	18.0-22.0	2.3-2.8
Y22H	310-360	3.10-3.60	220-250	2.77-3.14	280-320	3.52-4.02	20.0-24.0	2.5-3.0
Y23	320-370	3.20-3.70	170-190	2.14-2.38	190-230	2.39-2.89	20.0-25.5	2.5-3.2
Y25	360-400	3.60-4.00	135-170	1.70-2.14	140-200	1.76-2.51	22.5-28.0	2.8-3.5
Y25BH	360-390	3.60-3.90	176-216	2.20-2.70	215-231	2.70-2.90	23.9-27.1	3.0-3.4
Y26H	360-390	3.60-3.90	220-250	2.77-3.14	225-255	2.83-3.21	23.0-28.0	2.9-3.5
Y27H	370-400	3.70-4.00	205-250	2.58-3.14	210-255	2.64-3.21	25.0-29.0	3.1-3.7
Y28	370-400	3.70-4.00	175-210	2.20-2.64	180-220	2.26-2.77	26.0-30.0	3.3-3.8
Y30	385-405	3.85-4.05	176-224	2.20-2.80	184-226	2.30-2.84	27.5-30.5	3.45-3.95
Y30BH	380-400	3.80-4.00	230-275	2.89-3.46	235-290	2.95-3.65	27.0-32.5	3.4-4.1
Y32	400-420	4.00-4.20	160-190	2.01-2.38	165-195	2.07-2.45	30.0-33.5	3.8-4.2
Y33	410-430	4.10-4.30	220-250	2.77-3.14	225-255	2.83-3.21	31.5-35.0	4.0-4.4
Y35	400-420	4.00-4.20	160-190	2.01-2.38	165-195	2.07-2.45	30.0-33.5	3.8-4.2
Y35H1	395-415	3.95-4.15	251-259	3.15-3.25	255-271	3.20-3.40	29.6-32.8	3.7-4.1
Y35H2	390-410	3.90-4.10	236-295	3.30-3.70	275-299	3.45-3.75	28.8-32.0	3.6-4.04
Y35H3	405-425	4.05-4.25	223-247	2.80-3.10	231-255	2.90-3.20	30.2-35.4	3.8-4.4
Y35H-4H	370-390	3.70-3.90	270-302	3.40-3.80	326-358	4.10-4.50	25.6-28.8	3.2-3.6
Y38B	410-430	4.10-4.30	251-275	3.15-3.45	255-279	3.20-3.50	31.8-35.0	4.0-4.4
Y38H	395-415	3.95-4.15	287-309	3.60-3.90	311-333	3.90-4.20	29.5-32.7	3.7-4.1
Y40E	370-390	3.70-3.90	279-301	3.50-3.80	382-414	4.80-5.20	25.6-29.4	3.2-3.6
Y40B	410-430	4.10-4.30	290-324	3.65-3.95	307-329	3.85-4.15	32.6-34.4	4.0-4.4
Y45E	420-440	4.20-4.40	318-342	4.00-4.30	386-410	4.85-5.15	33.5-36.5	4.2-4.6
Y45B	430-450	4.30-4.50	247-271	3.10-3.40	251-275	3.15-3.45	35.1-38.3	4.4-4.8

